



INDUSTRIAL FABRICS, INC.
Since 1981

HEADQUARTERS
 510 O' Neal Lane
 Baton Rouge, LA 70819

225-273-9600 (Phone)
 225-273-0440 (Fax)
 www.ind-fab.com (Web)

Geotextile Product Description Sheet

GT-112 Nonwoven Geotextile

GT -112 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. GT -112 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. GT-112 conforms to the physical property values listed below:

| PROPERTY | TEST METHOD | UNIT | M.A.R.V. (Minimum Average Roll Value) |
|-------------------------|-------------|---|--|
| Weight (Typical) | ASTM D 5261 | oz/yd ² (g/m ²) | 12.0 (407) |
| Grab Tensile | ASTM D 4632 | lbs (kN) | 300 (1.33) |
| Grab Elongation | ASTM D 4632 | % | 50 |
| Trapezoid Tear Strength | ASTM D 4533 | lbs (kN) | 115 (0.511) |
| CBR Puncture Resistance | ASTM D 6241 | lbs (kN) | 850 (3.78) |
| Permittivity* | ASTM D 4491 | sec ⁻¹ | 1.0 |
| Water Flow* | ASTM D 4491 | gpm/ft ² (l/min/m ²) | 75 (3055) |
| AOS* | ASTM D 4751 | US Sieve (mm) | 100 (0.150) |
| UV Resistance | ASTM D 4355 | %/hrs | 70/500 |

| PACKAGING | |
|------------------------------|-----------------------|
| Roll Dimensions (W x L) – ft | 12.5 x 360 / 15 x 300 |
| Square Yards Per Roll | 500 |
| Estimated Roll Weight – lbs | 375 |

* At the time of manufacturing. Handling may change these properties.

Made in U.S.A.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Industrial Fabrics, Inc. assumes no liability in connection with the use of this information.